K-AN 302-60

Lock AN 302-60

Свойства

Приложение	Screw locking without pretreatment
здравина	High strength
вискозност	Medium viscosity
термоустойчив	-60 °C to +180 °C



Указание

Други данни при запитване.

Описание

High-strength bonding of passive materials such as stainless steel or aluminium, no pre-treatment required.Thermal stability: -60 °C to +180 °C- Reduced assembly time- High strength- Handling strength: just 2 to 5 minutes- Final strength: just 2 to 4 hours- No need for pre-treatment with activator and therefore no additional emissions due to solvents

Артикул

Обозначение	размер на връзка
K- 07 10 04 52	50 ml
K- 07 10 04 51	250 ml

Въпреки най-старателната проверка не са изключени грешки и ние не поемаме гаранция за съдържащите се данни.