

TR WGE

PA 12 plastic pipe, soft

HANSA FLEX

Properties

Application	Control lines in hydraulics and pneumatics automotive technology laboratories and food industry
Special features	resistant to temperature and weatherproof low weight
Inner layer	Polyamide
Insert	none
Outer layer	Polyamide
Colour	yellow
Temp. min.	-60 °C
Temp. max.	100 °C
Temp. range	Temperature peaks up to 120°C
Media	Mineral oil Grease Propellants resistant to aqueous acids, alkalis and salts



Note

From 20 °C the pressure reduction factor is to be taken into account.

(Max. operating pressure = operating pressure x factor).

Temp.: 20°C / 30°C / 40°C / 50°C / 60°C / 70°C / 80°C / 90°C / 100°C / 110°C / 120°C
Factor: 1.00 / 0.83 / 0.72 / 0.64 / 0.57 /

0.52 / 0.47 / 0.44 / 0.36 / 0.32 / 0.28

Item

Identification	Internal Ø (mm)	External Ø (mm)	Wall thickness (mm)	BD* at 20°C (bar)	Min. bending radius (mm)
TR 04-0.5 WGE	3,0	4,0	0,50	19,0	20
TR 04-0.65 WGE	2,7	4,0	0,65	26,0	20
TR 04-1 WGE	2,0	4,0	1,00	45,0	20
TR 05-0.85 WGE	3,3	5,0	0,85	28,0	25
TR 05-1 WGE	3,0	5,0	1,00	34,0	25
TR 06-1 WGE	4,0	6,0	1,00	27,0	30
TR 08-1 WGE	6,0	8,0	1,00	19,0	40
TR 08-1.25 WGE	5,5	8,0	1,25	26,0	40
TR 08-1.5 WGE	5,0	8,0	1,50	31,0	40
TR 10-1 WGE	8,0	10,0	1,00	15,0	60
TR 10-1.25 WGE	7,5	10,0	1,25	19,0	60
TR 10-1.5 WGE	7,0	10,0	1,50	23,0	50
TR 10-2 WGE	6,0	10,0	2,00	34,0	50
TR 12-1 WGE	10,0	12,0	1,00	12,0	60
TR 12-1.5 WGE	9,0	12,0	1,50	19,0	60
TR 12.5-1.25 WGE	10,0	12,5	1,25	15,0	75
TR 12-2 WGE	8,0	12,0	2,00	27,0	60
TR 14-1.5 WGE	11,0	14,0	1,50	16,0	80
TR 14-2 WGE	10,0	14,0	2,00	22,0	75
TR 15-1.5 WGE	12,0	15,0	1,50	15,0	90
TR 16-2 WGE	12,0	16,0	2,00	19,0	95
TR 18-2 WGE	14,0	18,0	2,00	16,0	100
TR 20-2 WGE	16,0	20,0	2,00	14,0	120
TR 22-2 WGE	18,0	22,0	2,00	13,0	150
TR 25-2.5 WGE	20,0	25,0	2,50	14,0	150
TR 28-2.5 WGE	23,0	28,0	2,50	13,0	150
TR 30-2.5 WGE	25,0	30,0	2,50	8,0	260

BD = Working pressure

Product versions

TR WB	PA 12 plastic pipe, soft, blue
TR WR	PA 12 plastic pipe, soft, red
TR WS	PA 12 plastic pipe, soft, black
TR WT	PA 12 plastic pipe, soft, Transparent