


Properties

| | |
|------------------|---|
| Application | Agricultural technology Construction industry Systems engineering |
| Special features | ozone, oil resistant and weatherproof |
| Inner layer | EPDM |
| Insert | synthetic threads |
| Outer layer | Chloroprene rubber |
| Colour | black |
| Temp. min. | -40 °C |
| Temp. max. | 120 °C |



Item

| Identification | Inches | Internal Ø (mm) | External Ø (mm) | Wall thickness (mm) | Operating pressure (bar) | Burst pressure (bar) | Min. bending radius (mm) |
|--------------------------|--------|--------------------|--------------------|------------------------|-----------------------------|-------------------------|-----------------------------|
| MULTI 13-3.2 EPDM | 1/2" | 13,0 | 19,4 | 3,2 | 30,0 | 90 | 130 |
| MULTI 19-4.2 EPDM | 3/4" | 19,0 | 27,4 | 4,2 | 25,0 | 75 | 190 |
| MULTI 25-4.5 EPDM | 1" | 25,0 | 34,0 | 4,5 | 20,0 | 60 | 250 |
| MULTI 32-5.5 EPDM | 1 1/4" | 32,0 | 43,0 | 5,5 | 12,0 | 36 | 320 |
| MULTI 38-6 EPDM | 1 1/2" | 38,0 | 50,0 | 6,0 | 12,0 | 36 | 380 |
| MULTI 51-8.5 EPDM | 2" | 50,8 | 68,0 | 8,6 | 7,0 | 70 | 510 |