
PVC WAS ELAST

PVC water hose



Properties					
Application	Agricultural technology				
Special features	durable resistant to pressure and abrasion flexible weatherproof				
Standard	ISO 1307				
Inner layer	stable, high flexibility, smooth plasticised PVC				
Insert	impact and pressure resistant PVC reinforcing spiral				
Outer layer	slightly ribbed outer surface				
Temp. min.	-20 °C				
Temp. max.	50 °C				
Media	Water				



Item									
Identification	Inches	Internal Ø	BD* at 20°C (bar)	Burst pressure (bar)	Vacuum (bar)	Min. bending radius	Roll length		
PVC WAS 25 ELAST	1"	25	7,0	20	0,9	90	50		
PVC WAS 32 ELAST	1.1/4"	32	6,0	17	0,9	130	50		
PVC WAS 38 ELAST	1.1/2"	38	6,0	16	0,9	140	50		
PVC WAS 51 ELAST	2"	51	5,0	15	0,9	200	50		
PVC WAS 63 ELAST	2.1/2"	63	4,5	14	0,9	275	50		
PVC WAS 76 ELAST	3"	76	4,0	12	0,9	310	50		
PVC WAS 90 ELAST	3.1/2"	90	3,5	10	0,9	375	50		
PVC WAS 102 ELAST	4"	102	3,0	10	0,9	410	20 / 30		
PVC WAS 110 ELAST	4.3/8"	110	3,0	10	0,9	450	20 / 30		
PVC WAS 127 ELAST	5"	127	2,5	9	0,9	520	20 / 30		
PVC WAS 152 ELAST	6"	152	2,0	9	0,9	610	15		

BD = Working pressure