


Properties						
Application	Coolant (air conditioning technology)					
Design	for screw fittings					
Standard	SAE J2064					
Inner layer	Butyl = R134a effusion values 65% lower than required according to SAEJ2064.					
Insert	very strong steel wire braid					
Outer layer	CR = Moisture absorption values 75% lower than required according to SAEJ2064					
Colour	black					
Temp. min.	-40 °C					
Temp. max.	120 °C					
Media	Compressor oils: PAG, ester only for TRITON SE55, SEZ80, Solest oil 35 / 68 Coolants: R134a					



Item								
Identification	DN*	Size	Inches	Internal Ø	External Ø	Operating pressure (bar)	Burst pressure (bar)	Min. bending radius
MD 120 AC	22	16	7/8"	22,8	31,3	35,0	175	160
MD 125 AC	28	20		29,3	38,3	35,0	175	195
MD 132 AC	35	24	1.3/8"	35,5	45,6	35,0	175	225

DN = Nominal diameter, nominal width