

K-AN 302-60

Lock AN 302-60

HANSA FLEX

Características

| | |
|----------------------------|------------------------------------|
| Aplicación | Screw locking without pretreatment |
| Resistencia | High strength |
| Viscosidad | Medium viscosity |
| Resistencia térmica | -60 °C to +180 °C |



Nota

Otras especificaciones a petición.

Descripción

High-strength bonding of passive materials such as stainless steel or aluminium, no pre-treatment required. Thermal stability: -60 °C to +180 °C- Reduced assembly time- High strength- Handling strength: just 2 to 5 minutes- Final strength: just 2 to 4 hours- No need for pre-treatment with activator and therefore no additional emissions due to solvents

Artículo

| Denominación | Tamaño de contenedor |
|----------------|----------------------|
| K- 07 10 04 52 | 50 ml |
| K- 07 10 04 51 | 250 ml |