

INDU WAS SD

Usisno tlačno crijevo za vodu

HANSA FLEX

Karakteristike

| | |
|-------------------|--|
| Područje primjene | Niskotlačna crijeva usisnih i tlačnih sustava Industrija i građevinsko obrtništvo |
| Norma | ISO 1307 |
| Unutrašnji sloj | prirodni i sintetički guma |
| Umetak | jako čvrsti, sintetički tekstilni umetak i spirala od čelične žice |
| Vanjski sloj | sintetička guma |
| Boja | crna |
| Temperatura min. | -25 °C |
| Temperatura max. | 70 °C |
| Mediji | Voda |



Artikli

| Naziv | Col | Unutarnji Ø (mm) | Vanjski Ø (mm) | Debljina stjenki (mm) | Radni tlak (bar) | Tlak pucanja (bar) | Vakuum (bar) | Radius savijanja min. (mm) | Duljina valjaka (m) |
|----------------------|--------|---------------------|-------------------|--------------------------|---------------------|-----------------------|-----------------|----------------------------------|------------------------|
| INDU WAS 25-5 SD | 1" | 25,4 | 35 | 5,0 | 10,0 | 30 | 0,93 | 153 | 40 |
| INDU WAS 32-5 SD | 1.1/4" | 32,0 | 42 | 5,0 | 10,0 | 30 | 0,93 | 192 | 40 |
| INDU WAS 38-5 SD | 1.1/2" | 38,0 | 48 | 5,0 | 10,0 | 30 | 0,93 | 228 | 40 |
| INDU WAS 45-5 SD | 1.3/4" | 44,5 | 55 | 5,0 | 10,0 | 30 | 0,93 | 267 | 40 |
| INDU WAS 51-5.5 SD | 2" | 51,0 | 62 | 5,5 | 10,0 | 30 | 0,93 | 306 | 40 |
| INDU WAS 63-6 SD | 2.1/2" | 63,5 | 75 | 6,0 | 10,0 | 30 | 0,93 | 381 | 40 |
| INDU WAS 70-8 SD | 2.3/4" | 70,0 | 86 | 8,0 | 10,0 | 30 | 0,93 | 420 | 40 |
| INDU WAS 76-6.5 SD | 3" | 75,0 | 89 | 7,0 | 10,0 | 30 | 0,93 | 458 | 40 |
| INDU WAS 102-6.5 SD | 4" | 101,6 | 115 | 6,5 | 10,0 | 30 | 0,93 | 610 | 40 |
| INDU WAS 127-8.5 SD | 5" | 127,0 | 144 | 8,5 | 10,0 | 30 | 0,93 | 762 | 40 |
| INDU WAS 152-8.5 SD | 6" | 152,4 | 169 | 8,5 | 10,0 | 30 | 0,93 | 915 | 40 |
| INDU WAS 203-10.5 SD | 8" | 203,2 | 224 | 10,5 | 10,0 | 30 | 0,93 | 1219 | 40 |
| INDU WAS 254-16 SD | 10" | 254,0 | 275 | 16,0 | 10,0 | 30 | 0,93 | 1524 | 40 |