


### Karakteristike

<b>Područje primjene</b>	Upravljački vodovi u hidraulici i pneumatici Tehnika vozila Laboratoriji i prehrambena industrija
<b>Posebna obilježja</b>	otporno na temperature i vremenske utjecaje mala težina
<b>Unutrašnji sloj</b>	Poliamid
<b>Umetak</b>	nema
<b>Vanjski sloj</b>	Poliamid
<b>Boja</b>	prozirno
<b>Temperatura min.</b>	-60 °C
<b>Temperatura max.</b>	100 °C
<b>Temperaturno područje</b>	najviše temperature do 120°C
<b>Mediji</b>	mineralno ulje mast pogonska goriva postojan na vodenaste kiseline, lužine i soli



### Napomena

Od 20 °C potrebno je obratiti pozornost na faktor smanjenja tlaka.<br>

(Maks. radni tlak = radni tlak x faktor).<br>

Temp.: 20°C / 30°C / 40°C / 50°C / 60°C / 70°C / 80°C / 90°C / 100°C / 110°C / 120°C<br>

Faktor: 1,00 / 0,83 / 0,72 / 0,64 / 0,57 / 0,52 / 0,47 / 0,44 / 0,36 / 0,32 / 0,28

### Artikli

Naziv	Unutarnji Ø (mm)	Vanjski Ø (mm)	Debljina stjenki (mm)	BD* kod 20°C (bar)	Radijus savijanja min. (mm)
TR 04-0.5 WT	3,0	4,0	0,500	19,0	20
TR 04-0.65 WT	2,7	4,0	0,650	26,0	20
TR 04-1 WT	2,0	4,0	1,000	44,0	20
TR 05-0.85 WT	3,3	5,0	0,850	28,0	25
TR 05-1 WT	3,0	5,0	1,000	34,0	25
TR 06-1 WT	4,0	6,0	1,000	27,0	30
TR 06-1.5 WT	3,0	6,0	1,500	45,0	30
TR 08-1 WT	6,0	8,0	1,000	19,0	40
TR 08-1.5 WT	5,0	8,0	1,500	31,0	40
TR 08-2 WT	4,0	8,0	2,000	45,0	40
TR 10-1 WT	8,0	10,0	1,000	15,0	60
TR 10-1.25 WT	7,5	10,0	1,250	19,0	60
TR 10-2 WT	6,0	10,0	2,000	34,0	50
TR 12-1 WT	10,0	12,0	1,000	12,0	55
TR 12-1.5 WT	9,0	12,0	1,500	19,0	60
TR 12-2 WT	8,0	12,0	2,000	27,0	60
TR 12.5-1.25 WT	10,0	12,5	1,250	15,0	75
TR 14-1.5 WT	11,0	14,0	1,500	16,0	80
TR 15-1.5 WT	12,0	15,0	1,500	15,0	90
TR 18-2 WT	14,0	18,0	2,000	16,0	100
TR 20-2 WT	16,0	20,0	2,000	14,0	120
TR 22-2 WT	18,0	22,0	2,000	13,0	150
TR 25-2.5 WT	20,0	25,0	2,500	14,0	150
TR 28-2.5 WT	23,0	28,0	2,500	13,0	150
TR 30-2.5 WT	25,0	30,0	2,500	8,0	260

BD = radni tlak