# WAS STRAHL

Tubazioni idriche per l'edilizia

## Caratteristiche




| | |
|---|---|
| **Caratteristiche particolari** | altamente flessibile e robusto<br>LABS-frei, privi di separatori e grassi<br>Basse perdite di carico |
| **Strato interno** | Strato interno EDPM nero, liscia, non poroso |
| **Inserzioni** | Fili sintetici |
| **Strato esterno** | EPDM (gomma etilene propilene)<br>insensibile all'ozono e ai raggi UV |
| **Colore** | nero |
| **Temperatura min.** | -40 °C |
| **Temperatura max.** | 95 °C |
| **Campo della temperatura:** | Picchi di temperatura fino a 110° C |
| **Mezzi** | Acqua |

## Nota

La pressione d'esercizio à riferita alla temperatura ambiente

## Articolo

| Denominazione | pollice | Ø interno (mm) | Spessore parete (mm) | Pressione d'esercizio (bar) | Raggio di curvatura min. (mm) | Lunghezza rullo (m) |
|---|---|---|---|---|---|---|
| **WAS 10-3.5 STRAHL** | 3/8" | 10 | 3,5 | 20,0 | 60 | 50 |
| **WAS 13-3 STRAHL** | 1/2" | 13 | 3,0 | 20,0 | 80 | 40 |
| **WAS 16-3.5 STRAHL** | 5/8" | 16 | 3,5 | 20,0 | 100 | 40 |
| **WAS 19-4 STRAHL** | 3/4" | 19 | 4,0 | 20,0 | 120 | 40 |
| **WAS 25-4.5 STRAHL** | 1" | 25 | 4,5 | 20,0 | 150 | 40 |
| **WAS 32-6 STRAHL** | 1.1/4" | 32 | 6,0 | 20,0 | 200 | 50 |

*Nonostante il più attento esame non si possono escludere eventuali errori ed omissioni, non ci assumiamo alcuna responsabilità per le indicazioni contenute.*