

K-TR POLYURETHAN

Polyurethane hose (PUR)

HANSA FLEX

Caratteristiche

| | |
|----------------------|-------------------------|
| Pressione di lavoro | Max. 10 bar (at +20 °C) |
| Durezza | 52 Shore D±3 |
| Calibratura | External |
| Temperatura ambiente | -35 °C to +80 °C |
| Materiale | Poliuretano |



Nota

Altri dati su richiesta.

Descrizione

This externally calibrated plastic hose made of high-quality polyester PUR is extremely flexible with optimal mechanical characteristics and very high pressure resistance across a wide temperature range. It is permanently flexible, boasts very good resilience and can be laid with a narrow bending radius. Its other advantages include good abrasion resistance, very good low-temperature flexibility and very high elongation at break. The hose is also suitable for vacuum applications. It is resistant to many different oils and lubricants (a special resistance test is recommended in specific cases owing to the additives that are blended in by the manufacturers), aliphatic hydrocarbons and gases such as oxygen, ozone, helium, etc.

Articolo

| Denominazione | Ø tubo flessibile interno (mm) | Ø tubo flessibile esterno (mm) | Raggio di curvatura rilevante per la portata (mm) | Colore | Lunghezza rullo (m) |
|----------------|--------------------------------|--------------------------------|---|---------|---------------------|
| K- 07 10 05 47 | 2,6 | 4,0 | 17 | Natural | 25 |
| K- 07 10 05 49 | 3,1 | 5,0 | 15 | Natural | 100 |
| K- 07 10 05 48 | 3,1 | 5,0 | 15 | blu | 100 |
| K- 07 10 05 51 | 9,0 | 12,0 | 67 | Natural | 100 |
| K- 07 10 05 52 | 9,0 | 12,0 | 67 | nero | 100 |
| K- 07 10 05 54 | 9,8 | 14,0 | 72 | Natural | 50 |
| K- 07 10 05 53 | 9,8 | 14,0 | 72 | blu | 50 |
| K- 07 10 05 55 | 9,8 | 14,0 | 72 | nero | 50 |
| K- 07 10 05 56 | 11,0 | 16,0 | 88 | Natural | 50 |
| K- 07 10 05 57 | 11,0 | 16,0 | 88 | nero | 50 |