

K-AN 302-60

Lock AN 302-60

HANSA FLEX

Características

Aplicação	Screw locking without pretreatment
Resistência	High strength
Viscosidade	Medium viscosity
Resistente à temperatura	-60 °C to +180 °C



Nota

Outras indicações a pedido.

Descrição

High-strength bonding of passive materials such as stainless steel or aluminium, no pre-treatment required. Thermal stability: -60 °C to +180 °C- Reduced assembly time- High strength- Handling strength: just 2 to 5 minutes- Final strength: just 2 to 4 hours- No need for pre-treatment with activator and therefore no additional emissions due to solvents

Artigo

Descrição	Tamanho da embalagem
K- 07 10 04 52	50 ml
K- 07 10 04 51	250 ml