K-AN 302-60

Lock AN 302-60

Vlastnosti

Použitie	Screw locking without pretreatment
Pevnosť	High strength
Viskozita	Medium viscosity
Odolný proti teplote	-60 °C to +180 °C



Poznámka

Ďalšie údaje na vyžiadanie.

Popis

High-strength bonding of passive materials such as stainless steel or aluminium, no pre-treatment required.Thermal stability: -60 °C to +180 °C- Reduced assembly time- High strength- Handling strength: just 2 to 5 minutes- Final strength: just 2 to 4 hours- No need for pre-treatment with activator and therefore no additional emissions due to solvents

Výrobok

Označenie	Veľkosť zväzku
K- 07 10 04 52	50 ml
K- 07 10 04 51	250 ml