

# K-TR POLYURETHAN

Polyurethane hose (PUR)

**HANSA FLEX**

## Lastnosti

|                     |                         |
|---------------------|-------------------------|
| delovni tlak        | Max. 10 bar (at +20 °C) |
| trdota              | 52 Shore D±3            |
| kalibriranje        | External                |
| temperatura okolice | -35 °C to +80 °C        |
| Material:           | poliuretan              |



## Navodilo

Drugi podatki na zahtevo.

## Opis

This externally calibrated plastic hose made of high-quality polyester PUR is extremely flexible with optimal mechanical characteristics and very high pressure resistance across a wide temperature range. It is permanently flexible, boasts very good resilience and can be laid with a narrow bending radius. Its other advantages include good abrasion resistance, very good low-temperature flexibility and very high elongation at break. The hose is also suitable for vacuum applications. It is resistant to many different oils and lubricants (a special resistance test is recommended in specific cases owing to the additives that are blended in by the manufacturers), aliphatic hydrocarbons and gases such as oxygen, ozone, helium, etc.

## Artikel

| Opis           | Ø cevi znotraj (mm) | Ø cevi zunaj (mm) | krivinski polmer relevanten za pretok (mm) | Barva   | Dolžina valjev (m) |
|----------------|---------------------|-------------------|--|---------|--------------------|
| K- 07 10 05 47 | 2,6                 | 4,0               | 17   | Natural | 25                 |
| K- 07 10 05 49 | 3,1                 | 5,0               | 15   | Natural | 100                |
| K- 07 10 05 48 | 3,1                 | 5,0               | 15   | modro   | 100                |
| K- 07 10 05 51 | 9,0                 | 12,0              | 67   | Natural | 100                |
| K- 07 10 05 52 | 9,0                 | 12,0              | 67   | črno    | 100                |
| K- 07 10 05 54 | 9,8                 | 14,0              | 72   | Natural | 50                 |
| K- 07 10 05 53 | 9,8                 | 14,0              | 72   | modro   | 50                 |
| K- 07 10 05 55 | 9,8                 | 14,0              | 72   | črno    | 50                 |
| K- 07 10 05 56 | 11,0                | 16,0              | 88   | Natural | 50                 |
| K- 07 10 05 57 | 11,0                | 16,0              | 88   | črno    | 50                 |