


## Osobine

<b>Oblast primene</b>	Upravljački vodovi u hidraulici i pneumatici Proizvodnja posuda i aparata Laboratorijska tehnika
<b>Posebne karakteristike</b>	postojanost na temperaturu i vremenske uticaje mala težina
<b>Pogled iznutra</b>	polietilen
<b>Umetak</b>	bez
<b>spoljni izgled</b>	polietilen
<b>Boja</b>	žuta
<b>Temperatura min.</b>	-10 °C
<b>Temperatura max.</b>	60 °C
<b>Mediji</b>	mineralno ulje Mast Pogonski materijali postojano na vodnjikave kiseline, razređene baze i soli kao i mnoštvo rastvarača



## Napomena

Od 20 °C potrebno je obratiti pažnju na faktor smanjivanja pritiska.<br>

(maks. radni pritisak = radni pritisak x faktor).<br>

Temp.: 20 °C / 30 °C / 40 °C / 50 °C / 60 °C<br>Factor: 1,00 / 0,83 / 0,72 / 0,64 / 0,57

## Artikal

Naziv	Unutrašnji-Ø (mm)	Spoljni-Ø (mm)	Debljina zida (mm)	BD* pri 20°C (bar)	min. radijus savijanja (mm)
TRPE 04-0.5 WGE	3,0	4	0,50	9	20
TRPE 04-0.65 WGE	2,7	4	0,65	13	20
TRPE 04-1 WGE	2,0	4	1,00	20	20
TRPE 05-1 WGE	3,0	5	1,00	15	25
TRPE 06-1 WGE	4,0	6	1,00	13	30
TRPE 08-1 WGE	6,0	8	1,00	8	40
TRPE 08-1.5 WGE	5,0	8	1,50	13	40
TRPE 10-1 WGE	8,0	10	1,00	6	60
TRPE 10-1.5 WGE	7,0	10	1,50	10	50
TRPE 10-2 WGE	6,0	10	2,00	15	50
TRPE 12-1 WGE	10,0	12	1,00	5	85
TRPE 12-1.5 WGE	9,0	12	1,50	9	60
TRPE 12-2 WGE	8,0	12	2,00	12	60
TRPE 14-1.5 WGE	11,0	14	1,50	8	80
TRPE 14-2 WGE	10,0	14	2,00	9	80
TRPE 15-1.5 WGE	12,0	15	1,50	7	90
TRPE 16-2 WGE	12,0	16	2,00	8	120
TRPE 18-2 WGE	14,0	18	2,00	7	120
TRPE 20-2 WGE	16,0	20	2,00	6	120
TRPE 22-2 WGE	18,0	22	2,00	5	150
TRPE 25-2.5 WGE	20,0	25	2,50	6	150
TRPE 30-2.5 WGE	25,0	30	2,50	5	260

BD = radni pritisak

## Varijante proizvoda

<b>TRPE WB</b>	Crevo od polietilena, plava
<b>TRPE WR</b>	Crevo od polietilena, crvena
<b>TRPE WS</b>	Crevo od polietilena, crna
<b>TRPE WT</b>	Crevo od polietilena, transparentno