


PVC WAS

Crevo za vodu od PVC-a

HANSA FLEX

Osobine

| | |
|-------------------------------|---|
| Oblast primene | Građevinska industrija Agrarna tehnika |
| Posebne karakteristike | veoma izdržljivo, savitljivo, čvrsto na pritisak i habanje, postojano na UV zrake i vremenske uticaje lako rebrasti spoljni omot |
| Pogled iznutra | plastificirani PVC, stabilan, veoma fleksibilan, gladak |
| Umetak | spirala za pojačanje od PVC-a otpornog na pritisak i udarce |
| spoljni izgled | plastificirani PVC, stabilan, veoma fleksibilan, gladak |
| Temperatura min. | -5 °C |
| Temperatura max. | 60 °C |
| Mediji | voda |



Napomena

Npr. sve oznake sa "-6" ne odnose se na debljinu zida

Artikal

| Naziv | col | Unutrašnji-Ø (mm) | Debljina zida (mm) | BD* pri 20°C (bar) | Razorni pritisak (bar) | Vakuum (bar) | min. radijus savijanja (mm) | Dužina rolne (m) |
|----------------|--------|----------------------|-----------------------|-----------------------|---------------------------|-----------------|--------------------------------|---------------------|
| PVC WAS 19-6 | 3/4" | 19 | 3,0 | 8,0 | 25 | 0,7 | 85 | 50 |
| PVC WAS 25-7 | 1" | 25 | 3,0 | 7,0 | 21 | 0,6 | 105 | 50 |
| PVC WAS 32-6 | 1.1/4" | 32 | 3,0 | 6,0 | 21 | 0,6 | 125 | 50 |
| PVC WAS 38-6 | 1.1/2" | 38 | 3,5 | 6,0 | 18 | 0,6 | 150 | 50 |
| PVC WAS 50-5 | 2" | 51 | 4,5 | 5,0 | 15 | 0,6 | 205 | 50 |
| PVC WAS 60-4.5 | 2.1/2" | 60 | 4,5 | 4,5 | 13 | 0,6 | 248 | 50 |
| PVC WAS 76-3.5 | 3" | 76 | 4,5 | 3,5 | 12 | 0,6 | 320 | 50 |
| PVC WAS 90-3.5 | 3.1/2" | 90 | 5,0 | 3,0 | 11 | 0,6 | 395 | 50 |

BD = radni pritisak