

BETON 40

Creva za transport betona

HANSA FLEX

Osobine

Oblast primene	Građevinska industrija
Posebne karakteristike	reljefno
Norma	DIN 53516
Pogled iznutra	izolir guma veoma otporna na habanje
Umetak	četiri tekstilna umetka veoma otporna na cepanje sa bakarnim nitima
spoljni izgled	sintetička guma, veoma otporna na habanje, delovanje ozona i atmosferskih prilika
Boja	crna
Temperatura min.	-40 °C
Temperatura max.	70 °C
Mediji	Malter, beton, estrih



Artikal

Naziv	col	Unutrašnji-Ø (mm)	Spoljni-Ø (mm)	Radni pritisak (bar)	Razorni pritisak (bar)	min. radijus savijanja (mm)	Dužina rolne (m)
BETON 40-25-38	1"	25,4	38,0	40,0	120	110	40
BETON 40-32-46	1.1/4"	32,0	46,0	40,0	120	160	40
BETON 40-35-49	1.3/8"	35,0	49,0	40,0	120	175	40
BETON 40-38-54	1.1/2"	38,0	54,0	40,0	120	190	40
BETON 40-50-68	2"	50,8	68,0	40,0	120	280	40
BETON 40-63.5-83.5	2.1/2"	63,5	83,5	40,0	120	375	40