

# NY 500

Termoplastično crevo za visoki pritisak

**HANSA FLEX**

## Osobine

Oblast primene	Hemijska industrija
Pogled iznutra	Polyamide (PA)
Umetak	one or two textile layers of aramide-fiber and a steel wire braided insert
spoljni izgled	poliuretan
Boja	crna
Temperatura min.	-40 °C
Temperatura max.	100 °C
Temperaturni opseg	limited to +70°C for air and water based fluids
Mediji	Rastvarači



## Dodatne informacije

Sigurnost: 4 : 1

## Artikal

Naziv	DN*	Veličina	col	Unutrašnji-Ø (mm)	Spoljni-Ø (mm)	Radni pritisak (bar)	Razorni pritisak (bar)	min. radijus savijanja (mm)
NY 506	6	4	1/4"	6,6	12,7	700,0	2800	35
NY 508	8	5	5/16"	8,1	16,0	700,0	2800	60
NY 510	10	6	3/8"	9,8	18,7	700,0	2800	90
NY 513	12	8	1/2"	13,0	23,2	590,0	2360	100
NY 516	16	10	5/8"	16,3	26,6	500,0	2000	160
NY 520	19	12	3/4"	19,5	30,5	450,0	1800	180
NY 525	25	16	1"	25,8	38,1	315,0	1260	250

DN = nominalni prečnik, nominalna širina