K-AN 302-60

Lock AN 302-60

Osobine

Primena	Screw locking without pretreatment
Čvrtoća	High strength
Viskozitet	Medium viscosity
Otporan za temperaturu	-60 °C to +180 °C



Napomena

Ostali podaci na upit.

Opis

High-strength bonding of passive materials such as stainless steel or aluminium, no pre-treatment required.Thermal stability: -60 °C to +180 °C- Reduced assembly time- High strength- Handling strength: just 2 to 5 minutes- Final strength: just 2 to 4 hours- No need for pre-treatment with activator and therefore no additional emissions due to solvents

Artikal

Naziv	Veličina posude
K- 07 10 04 52	50 ml
K- 07 10 04 51	250 ml

Uprkos pažljivom proveravanju, ne možemo isključiti greške i ne preuzimamo nikakvu garanciju za navedene podatke.