


### 属性

应用范围	液压气动控制管路 汽车行业 实验室和食品行业
特殊的属性	耐低温,耐恶劣天气 重量轻
内胶层	聚酰胺
增强层	没有
外胶层	聚酰胺
颜色	黑色
温度 min.	-60 °C
温度 max.	100 °C
温度范围	温度峰值至120°C
适用介质	矿物油 油脂 燃料 耐受酸,耐碱和盐类溶液



### 提示

从20 °C起请注意压力减小系数。<br>

(最大工作压力 = 工作压力 x 系数)。<br>

温度:20°C / 30°C / 40°C / 50°C / 60°C / 70°C / 80°C / 90°C / 100°C / 110°C / 120°C<br>

因数:1,00 / 0,83 / 0,72 / 0,64 / 0,57 / 0,52 / 0,47 / 0,44 / 0,36 / 0,32 / 0,28

### 货品

名称	内径-Ø (mm)	外径Ø (mm)	壁厚 (mm)	BD* 20°C下 (bar)	最小弯曲半径 (mm)
TR 04-0.5 WS	3,0	4,0	0,50	19,0	20
TR 04-0.65 WS	2,7	4,0	0,65	26,0	20
TR 04-1 WS	2,0	4,0	1,00	45,0	20
TR 05-0.85 WS	3,3	5,0	0,85	28,0	25
TR 05-1 WS	3,0	5,0	1,00	34,0	25
TR 06-1 WS	4,0	6,0	1,00	27,0	30
TR 06-1.5 WS	3,0	6,0	1,50	45,0	30
TR 08-1 WS	6,0	8,0	1,00	19,0	40
TR 08-1.25 WS	5,5	8,0	1,25	26,0	40
TR 08-1.5 WS	5,0	8,0	1,50	31,0	40
TR 08-2 WS	4,0	8,0	2,00	45,0	40
TR 09-1.5 WS	6,0	9,0	1,50	27,0	45
TR 10-1 WS	8,0	10,0	1,00	15,0	60
TR 10-1.25 WS	7,5	10,0	1,25	19,0	60
TR 10-1.5 WS	7,0	10,0	1,50	23,0	50
TR 10-2 WS	6,0	10,0	2,00	34,0	50
TR 11-1.5 WS	8,0	11,0	1,50	21,0	55
TR 12-1 WS	10,0	12,0	1,00	12,0	55
TR 12-1.5 WS	9,0	12,0	1,50	19,0	60
TR 12-2 WS	8,0	12,0	2,00	27,0	60
TR 12.5-1.25 WS	10,0	12,5	1,25	15,0	75
TR 14-1.5 WS	11,0	14,0	1,50	16,0	80
TR 14-2 WS	10,0	14,0	2,00	22,0	75
TR 15-1.5 WS	12,0	15,0	1,50	15,0	90
TR 16-2 WS	12,0	16,0	2,00	19,0	95
TR 18-2 WS	14,0	18,0	2,00	16,0	100
TR 20-2 WS	16,0	20,0	2,00	14,0	120
TR 22-2 WS	18,0	22,0	2,00	13,0	150
TR 25-2.5 WS	20,0	25,0	2,50	14,0	150
TR 28-2.5 WS	23,0	28,0	2,50	13,0	150

BD = 工作压力

### 产品变体

TR WB	PA 12材料制成的塑料管,软, 蓝色
TR WGE	PA 12材料制成的塑料管,软, 黄色
TR WR	PA 12材料制成的塑料管,软, 红色
TR WT	PA 12材料制成的塑料管,软, 透明无色