


PVC WAS

PVC材料的水软管



| 属性 | |
|---------|------------------------------------|
| 应用范围 | 建筑工业 农业技术 |
| 特殊的属性 | 极其耐用、可弯曲、抗压和抗磨损、耐紫外线和耐气候带轻微突起条纹的外壳 |
| 内胶层 | 结实、高度柔韧、光滑的塑化PVC |
| 增强层 | 抗冲抗压PVC加固螺旋线 |
| 外胶层 | 结实、高度柔韧、光滑的塑化PVC |
| 温度 min. | -5 °C |
| 温度 max. | 60 °C |
| 适用介质 | 水 |



提示
所有“-6”的名称都与墙厚度无关

| 货品 | | | | | | | | |
|----------------|--------|--------------|------------|--------------------|---------------|-------------|----------------|-----------|
| 名称 | 英寸 | 内径-Ø (mm) | 壁厚 (mm) | BD* 20°C下 (bar) | 破裂压力 (bar) | 真空 (bar) | 最小弯曲半径 (mm) | 卷长 (m) |
| PVC WAS 19-6 | 3/4" | 19 | 3,0 | 8,0 | 25 | 0,7 | 85 | 50 |
| PVC WAS 25-7 | 1" | 25 | 3,0 | 7,0 | 21 | 0,6 | 105 | 50 |
| PVC WAS 32-6 | 1.1/4" | 32 | 3,0 | 6,0 | 21 | 0,6 | 125 | 50 |
| PVC WAS 38-6 | 1.1/2" | 38 | 3,5 | 6,0 | 18 | 0,6 | 150 | 50 |
| PVC WAS 50-5 | 2" | 51 | 4,5 | 5,0 | 15 | 0,6 | 205 | 50 |
| PVC WAS 60-4.5 | 2.1/2" | 60 | 4,5 | 4,5 | 13 | 0,6 | 248 | 50 |
| PVC WAS 76-3.5 | 3" | 76 | 4,5 | 3,5 | 12 | 0,6 | 320 | 50 |
| PVC WAS 90-3.5 | 3.1/2" | 90 | 5,0 | 3,0 | 11 | 0,6 | 395 | 50 |

BD = 工作压力