


PVC WAS ELAST

PVC材料的水软管

HANSA FLEX

属性

| | |
|---------|----------------------------|
| 应用范围 | 农业技术 |
| 特殊的属性 | 耐用 抗压和抗磨损 可弯曲 耐气候 |
| 标准 | ISO 1307 |
| 内胶层 | 结实、高度柔韧、光滑的塑化PVC |
| 增强层 | 抗冲抗压PVC加固螺旋线 |
| 外胶层 | 带轻微突起条纹的外表面 |
| 温度 min. | -20 °C |
| 温度 max. | 50 °C |
| 适用介质 | 水 |



货品

| 名称 | 英寸 | 内径-Ø (mm) | BD* 20°C下 (bar) | 破裂压力 (bar) | 真空 (bar) | 最小弯曲半径 (mm) | 卷长 (m) |
|-------------------|--------|--------------|--------------------|---------------|-------------|----------------|-----------|
| PVC WAS 25 ELAST | 1" | 25 | 7,0 | 20 | 0,9 | 90 | 50 |
| PVC WAS 32 ELAST | 1.1/4" | 32 | 6,0 | 17 | 0,9 | 130 | 50 |
| PVC WAS 38 ELAST | 1.1/2" | 38 | 6,0 | 16 | 0,9 | 140 | 50 |
| PVC WAS 51 ELAST | 2" | 51 | 5,0 | 15 | 0,9 | 200 | 50 |
| PVC WAS 63 ELAST | 2.1/2" | 63 | 4,5 | 14 | 0,9 | 275 | 50 |
| PVC WAS 76 ELAST | 3" | 76 | 4,0 | 12 | 0,9 | 310 | 50 |
| PVC WAS 90 ELAST | 3.1/2" | 90 | 3,5 | 10 | 0,9 | 375 | 50 |
| PVC WAS 102 ELAST | 4" | 102 | 3,0 | 10 | 0,9 | 410 | 20 / 30 |
| PVC WAS 110 ELAST | 4.3/8" | 110 | 3,0 | 10 | 0,9 | 450 | 20 / 30 |
| PVC WAS 127 ELAST | 5" | 127 | 2,5 | 9 | 0,9 | 520 | 20 / 30 |
| PVC WAS 152 ELAST | 6" | 152 | 2,0 | 9 | 0,9 | 610 | 15 |

BD = 工作压力