



| 属性 | | | | | | | |
|---------|--------------------------|--|--|--|--|--|--|
| 应用范围 | 用于料仓运输车辆上水泥、沙子、砾石和颗粒的卸货。 | | | | | | |
| 特殊的属性 | 磨损值按照DIN 53516 < 65 mm3 | | | | | | |
| 标准 | ISO 1307 | | | | | | |
| 内胶层 | 高抗磨损绝缘橡胶 | | | | | | |
| 增强层 | 高抗断强度人造纤维织物衬里和铜绞线 | | | | | | |
| 外胶层 | 特殊合成橡胶,高抗磨损、耐臭氧和耐气候,带刺孔。 | | | | | | |
| 颜色 | 黑色 | | | | | | |
| 温度 min. | -40 °C | | | | | | |
| 温度 max. | 70 °C | | | | | | |
| 适用介质 | 水泥 沙子 砾石 颗粒 | | | | | | |



| 货品 | | | | | | | |
|--------------|--------|-------------------------|-------------|--------------------------|--------------------------|---------------------------|-----------|
| 名称 | 英寸 | 内径-Ø _(mm) | 外径Ø (mm) | 工作压力 ^(bar) | 破裂压力 ^(bar) | 最小弯曲半径 ^(mm) | 卷长 (m) |
| SILO 25-6 | 1" | 25,4 | 37,0 | 10,0 | 30 | 254 | 40 |
| SILO 32-6 | 1.1/4" | 32,0 | 44,0 | 10,0 | 30 | 320 | 40 |
| SILO 38-6 | 1.1/2" | 38,0 | 50,0 | 10,0 | 30 | 380 | 40 |
| SILO 51-6.5 | 2" | 50,8 | 64,5 | 10,0 | 30 | 508 | 40 |
| SILO 63-7 | 2.1/2" | 63,5 | 77,0 | 10,0 | 30 | 635 | 40 |
| SILO 76-7 | 3" | 76,2 | 90,0 | 10,0 | 30 | 762 | 40 |
| SILO 90-7 | 3.1/2" | 90,0 | 104,0 | 10,0 | 30 | 900 | 40 |
| SILO 102-8 | 4" | 101,6 | 118,0 | 10,0 | 30 | 1016 | 40 |
| SILO 127-9.5 | 5" | 127,0 | 146,0 | 10,0 | 30 | 1270 | 40 |
| SILO 152-10 | 6" | 152,4 | 172,0 | 10,0 | 30 | 1524 | 40 |
| SILO 203-11 | 8" | 203,2 | 225,0 | 10,0 | 30 | 2032 | 20 |
| SILO 254-11 | 10" | 254,0 | 276,0 | 10,0 | 30 | 2540 | 20 |